

Amendment to the Specification:

Please amend the paragraph beginning at page 7, line 16 of the specification as follows:

When the heating temperature is, for example, 180 degrees centigrade, the first resin 10 is preferably a resin having a melting point lower than 180 degrees centigrade. To be specific, a material that can be used is thermoplastic olefin rubber or general purpose plastic such as polypropylene (PP), polyethylene (PE), and polyurethane. The melting point of polypropylene is about 160 to 170 degrees centigrade, the melting point of linear low density polyethylene is about 130 degrees centigrade, and the melting point of polyurethane is about 130 degrees centigrade. On the other hand, the second resin 11 may be any material as long as it is a non-conductive resin which has a melting point of about 180 degrees centigrade or higher and can be thermally adhered to the first resin 10. For example, polyamide-based resin such as nylon 6 and nylon 66 can be used. In addition, for the second resin 11, it is possible to use polytetrafluoroethylene (PTFE), polyvinylidene fluoride, polystyrene, and the like, furthermore silicone rubber and the like. The melting point of nylon 6 is about 225 degrees centigrade, the melting point of nylon 66 is about 267 degrees centigrade, the melting point of ~~PTEF~~ PTFE is about 320 degrees centigrade, the melting point of polyvinylidene fluoride is about 210 degrees centigrade, and the melting point of polystyrene is about 230 degrees centigrade. Furthermore, the silicone rubber is usable at about 250 degrees centigrade.